



METALLO DURO



METALLO DURO

RCR 24


EdmW

SPECIAL
CORROSION FREE

WC	Co	TiC	TaC	Ni	Other
87%	12%				1%

Dok. Nr. : 224-14-04

Grade structure



Physical information

Average grain size	µm	Medium
Density	g/cm ³	14.15
Hardness	HV30	1400
Fracture strength	N/mm ² m ^(1/2)	13
Transverse rupture strength	N/mm ²	3200
Compressive strength	N/mm ²	5000
Young's modulus	kN/mm ²	560
Thermal conductivity	W/Mk	85
Thermal expansion	10 ⁻⁶ K	5.7

Tutti i dati riportati in queste schede sono puramente indicativi



Swiss made for you!
HARTMETALL ESTECH AG