

Material data sheet

SWG 738HH

material characteristics	material number / grade	SWG 738HH						
	short designation	25MnCrNiMoV6-6-4						
	comparable grade	AISI P20+Ni, 1.2738, 1.2738mod						
	chemical composition - reference analysis [%]	C	Si	Mn	Cr	Mo	Ni	others
		0.27	0.30	1.55	1.35	alloyed	1.00	alloyed
	production technology	EAF/LF/VD, forging, Q+T						
	service hardness / strength <small>converted acc. to DIN EN ISO 18265 table B2</small>		HB	HRC	N/mm ²			variation upon request
			324 - 359	34-38	1030 - 1140			
	delivery condition	Q+T	324 - 359	34-38	1030 - 1140			
	maximum dimension	diameter			thickness			
	-			≤ 800 mm				
US-specification	EN 10228-3			SEP 1921				
	table 3 - type 1 - qual. class 3			group 3 - class D,d				
cleanliness	DIN 50602			ASTM E45 Methode A				
	K4 ≤ 20			A ≤ 1,5; B, C, D ≤ 2				

technological properties		0	1	2	3	4	5	comment	
	toughness		■	■	■				in relation to service hardness
	hot strength at working temp.		■	■	■				
	wear resistance		■	■	■				
	corrosion resistance	■							
	machinability		■	■	■				Q+T
	polishability		■	■	■				ISO/SPI: N2/A-2; for high-polishing: XPM
	weldability		■	■	■	■			CET = 0.57 % acc. DIN EN 1011-2
	texturability		■	■	■				for high quality XPM
	nitridability		■	■	■				nitriding hardness 550 - 700 HV1
chrome-platability		■	■	■					

rating properties: 0 = not suitable; 1 = low; 2 = middle; 3 = good; 4 = very good; 5 = perfectly suitable

physical properties	thermal conductivity [W · m ⁻¹ · K ⁻¹]	20 °C	200 °C	300 °C	500 °C
		31.3	34.4	34.1	32.7
	coefficient of thermal expansion between 20 °C and ... [10 ⁻⁶ · K ⁻¹]	100 °C	200 °C	300 °C	500 °C
		11.8	12.5	13.1	14.8
	elastic modulus [kN/mm ²]	20 °C	200 °C	300 °C	500 °C
		212	207	192	175


application	technology	mold making, injection molding
	tools	plastic molds, large molds, large mold frames, die-holder
	process temperature	< 250 °C
	tool size	medium- and large-sized molds
	final products	car bumpers, large interior parts, plastic housings
	features	alternative to 1.2738 for large molds, for high surface requirements: XPM and XPM ESR

SWG processing instructions	welding, texturing
-----------------------------	--------------------


heat treatment		T min [°C]	T max [°C]	medium / comment
	annealing	710	740	air
	hardening	870	920	oil, polymer
	tempering	540	650	air
	stress relieving	500	530	max. 30 °C below tempering temp.
	pre-heating before welding	300	330	
	nitriding	450	530	max. 30 °C below tempering temperature
	PVD-treating	450	530	

diagrams/ structure	TTT-diagram	yes
	tempering diagram	yes
	advice on heat treatment	pre-hardened
	microstructure	mainly bainitic

Tempering diagram: Average values on samples dia 25 mm x length 50 mm; hardened at 880 °C in oil



TTT-diagram (continuous)



PLEASE NOTE: The information contained in this data sheet is unbinding. It merely serves the first orientation of the user. Therefore, we do not assume any liability for the correctness, completeness or up-to-dateness of such data. In case of an order, the properties of the product are exclusively subject to the provisions of the respective contract.
© Schmiedewerke Gröditz GmbH, Gröditz